

SELLACRYL 5X1



HIGH-SOLIDS, HIGH CONCENTRATION ECOLOGIC ACRYLIC PRIMER

PRODUCT DATA SHEET

DESCRIPTION

SELLACRYL 5 X 1 is an ecologic, LEED certified, concentrated, specially formulated styrene - acrylic primer that prepares most exterior surfaces for finish coats. It provides maximum breathability, adhesion, mildew resistance and holdout to prolong the life of the finish. It increases surface spread rate for any coating applied on top of it. Easily applicable, with great adherence, non-flammable, non-toxic, anti-fungi. It possesses very high adherence, hardness, and protection to a great variety of surfaces. It is 1-2 dichlorobenzene, Alkyl phenol, formaldehyde, lead, mercury, chromium, antimonium, triphenyl tin and tributyl tin free.

APPLICATION / RECOMMENDED USES

Liquid primer for any concrete, masonry block, brick, stucco, plywood, etc. surface. It prepares the surface for any latex coating, texture coating and roof coating. When diluting mix perfectly to obtain a homogeneous mixture.

AVAILABLE PRESENTATIONS

1 liter, 1 gallon, 5 gallons, and 200 liters.

SURFACE SPREAD AREA

-FOR LATEX PAINTS: 31 – 42 sq. meters per liter, diluted with 5 parts of water for every 1 part of primer.

-FOR LATEX TEXTURIZED COATING: 20 - 24 sq. meters per liter, diluted with 3 parts of water for every 1 part of primer.

-FOR ACRYLIC ROOF COATING: 13 – 16 sq. meters per liter, diluted with 2 parts of water for every 1 part of primer.

APPLICATION

Clean the surface perfectly leaving it grease and dust free. If needed, the surface must be sanded and / or brushed before primer to ensure a clean and proper surface. Use a coat of SELLACRYL 5x1

RECOMMENDATIONS

-Do not mix with any other products.
 -Do not leave any container without its lid or in the sun.
 -Wash your brushes and tools with water.

STORAGE

It can be stored in a dry, dark, and fresh place for up to one year as long as it is perfectly sealed in its original container. Do not store SELLACRYL 5X1 if it has already been diluted.

WARRANTY

PINTEX warrantees the quality of its products according to its specifications. SELLACRYL 5X1 has warranty as long as it is used following every recommendation made by PINTEX. Recommendations, yields, and suggestions enlisted above do not represent a warranty.

TECHNICAL DATA

VOC (NOM-123- SEMARNAT-1998)	Less than 150 g/L
Brookfield Viscosity (ASTM D 2196)	25,000 - 32,500 cps
Density (ASTM D 1475)	1.02 - 1.06 g/mL
% Solids by Weight (ASTM D 1644)	34 - 36
pH (ASTM - E70)	8 - 9.5

Data referred to in this Sheet is based solely on our experience. PINTEX is not responsible for any flaws or damages caused by existing conditions, whether on the surface or on the building itself. We recommend making tests before applying the products on any particular application. The warrantee is limited only to the exchange of the material to fix any flaw, not including labor or any other additional costs. The information contained herein may be changed without any prior notice.

Elaboration: 23 May 2003

Check day: 26 May 2011